
TEST REPORT n. 4503/2020/I

CERAMIC TILES - DETERMINATION OF RESISTANCE TO STAINS

UNI EN ISO 10545-14: 2015

Date of report:	11/12/2020
Customer:	NUOVOCORSO S.p.A. Via Mulini Valle Tresinaro, 11 42033 ZOCCADELLO DI ONFIANO - CARPINETI (RE)
Requested on:	11/04/2020
Our ref.number:	28787
Execution place of tests:	Scandiano (RE)
Description of the sample:	"Portion of ceramic tiles glazed 60x60 cm obtained by cutting to original size 160x320 cm marked: GLAZED PORCELAIN TILES RECTIFIED"
Sampling:	carried out by the customer
Receipt date of samples:	11/04/2020
Execution date of tests:	start: 11/10/2020 end: 11/11/2020
Test specification:	UNI EN ISO 10545 - 14:2015 Determination of resistance to stains
Warnings:	<i>This test report can not be reproduced in part, without our written consent. The reported results relate only to the samples tested. The information included in quotation marks was provided by the customer.</i>

TEST REPORT n. 4503/2020/I
CERAMIC TILES - DETERMINATION OF RESISTANCE TO STAINS
UNI EN ISO 10545-14: 2015

Principle: Determination of the resistance to stains by maintaining test solutions and materials in contact with the proper surface of the tiles for a suitable length of time; the surfaces are then subjected to defined cleaning methods, and finally inspected for visual changes.

N. samples tested: 5

Test results:

<u>Staining agents</u>	Sample 1 Class	Sample 2 Class	Sample 3 Class	Sample 4 Class	Sample 5 Class
<u>Stains leaving a trace (pastes)</u>					
Green staining agent in light oil	5	5	5	5	5
<u>Stains having chemical/oxidizing action</u>					
Iodine, alcoholic solution 13 g/l	5	5	5	5	5
<u>Stains forming a film</u>					
Olive oil	4	4	4	4	4

Classification procedure of the test of resistance to stains:

- Class 5: Procedure A, stain removed with warm water (55 ± 5) ° C, allowed to flow for 5 min
- Class 4: Procedure B, stain removed manually using a natural non-abrasive sponge and weak cleaning agent, (pH 6.5÷7.5) (Ajax liquid)
- Class 3: Procedure C, stain removed mechanically for 2 min using a strong cleaning agent containing abrasive (pH 9÷10) (Cif)
- Class 2: Procedure D, stain removed by immersing the sample in a suitable solvent for 24 hours.
- Class 1: Stain not removed



The Director
Giulia Gaido

End of the document